

## ABSTRACT OF THE DISCLOSURE

This invention relates to a process of manufacturing a cellulose molding, a plant component extracting apparatus and a process of manufacturing cellulose acetate. In one embodiment of the invention, the process of manufacturing a cellulose molding comprises steaming corncob meal at a temperature of 150 to 250°C and a pressure of 20 to 29 MPa, filtering the steamed corncob meal with a filtering device to obtain a solid and molding the solid.

S:\DOCS\HZC\HZC-4812.DOC  
031104